


PROMATECT®-H

Fire protective construction board



Product description

PROMATECT®-H is a non-combustible calcium silicate board manufactured under Promat's proprietary Mineral Matrix Engineering Technology. It does not contain formaldehyde or any asbestos. The product is dimensionally stable and resistant to the effects of moisture. Its performance characteristics are not degraded by moisture. PROMATECT®-H has the following intended uses (according to EAD(1) 350142-00-1106): internal use (type Z2), internal use in high humidity conditions (type Z1) and external semi-exposed use (type Y). For fully exposed conditions, consult Promat Technical Department.

Manufacturing Certification

PROMATECT®-H is manufactured under a quality management system certified in accordance with ISO 9001:2015. The manufacturing site is also certified to meet the environmental standards of ISO 14001:2015 and the occupational health & safety requirements of ISO 45001:2018.

EAD⁽¹⁾: European Assessment Document

Fire Resistant Applications

- Structural steel fire protection
- Internal drywalls
- Internal lining to external walls
- Suspended and self-supporting hanger free ceilings
- Self-supporting airduct or cladding to steel sheet metal ducts
- Enclosures to E&M services
- Smoke screens
- Flame barrier
- Parapet & spandrel walls
- Upgrading fire performance of
 - Reinforced concrete
 - Masonry construction

Material properties

General description	Calcium Silicate board made with Mineral Matrix Engineering technology
Surface condition & appearance	Off-white colour Front face: smooth Back face: sanded
Nominal dry density (average)	Approx. 975kg/m ³
Moisture Content	Approx. 6.0% The moisture content varies and will reach an equilibrium over time with the atmospheric relative humidity of the environment
Alkalinity	pH 12
Thickness tolerance	Compliant with thickness tolerance of CE requirements (9mm thick standard sheets, +/-0.5mm)
Dimension tolerance	±5mm (standard board dimensions)

Static Values

Modulus of Elasticity E	Flexural Strength F	Tensile strength T	Compressive strength \perp
Longitudinal: 4.1kN/mm ² Transverse: 4.0kN/mm ²	Longitudinal: 10N/mm ² Transverse: 7N/mm ²	Longitudinal: 4.11N/mm ² Transverse: 2.15N/mm ²	9.3N/mm ²

Reaction to Fire & Thermal Properties

Combustibility	Surface burning	Thermal conductivity
A1 Classification: EN 13501-1 Non-combustible: BS 476: Part 4	Class O: BS 476: Part 6 & 7	0.242W/m ² K

PROMATECT®-H

Fire protective construction board

Standard thickness	Standard dimension	Number of boards per pallet	Surface area per pallet	Weight of standard sheet	Weight per pallet
9mm	2440mm x 1220mm	61	181.5m ²	Approx. 29kg	Approx. 1,888kg
12mm	2440mm x 1220mm	46	136.9m ²	Approx. 39kg	Approx. 1,896kg
15mm	2440mm x 1220mm	36	107.3m ²	Approx. 49kg	Approx. 1,858kg
20mm	2440mm x 1220mm	27	80.4m ²	Approx. 65kg	Approx. 1,859kg
25mm	2440mm x 1220mm	22	65.4m ²	Approx. 82kg	Approx. 1,890kg

All physical and mechanical values are averages based on standard production and tested according to internal procedures. The typical values are given for guidance. The figures can change dependent on the test methods used. If a particular value is of prime importance for a specification, please consult Promat Technical Department.

Australia

Promat Australia Pty Ltd

South Australia office

1 Scotland Road
SA 5031 Mile End South
☎ 1800 Promat (776 628)
☎ +61 8 8352 1014
✉ PAPL.mail@etexgroup.com

New South Wales office

Unit 1, 175 Briens Road
Northmead, NSW 2152
☎ 1800 Promat (776 628)
☎ +61 2 9630 0258
✉ PAPL.mail@etexgroup.com

Victoria office

Suite 205, 198 Harbour Esplanade
Docklands, VIC 3008
☎ 1800 Promat (776 628)
☎ 1800 334 598
✉ PAPL.mail@etexgroup.com

Queensland office

433 Logan Road
Stones Corner, QLD 4120
☎ 1800 011 376
☎ 1800 334 598
✉ PAPL.mail@etexgroup.com

China

Promat Shanghai Ltd

No.2, Tai Hua Street
Yonghe Economic District
511356 Guangzhou Guangdong
☎ +86 20 8136 1167
☎ +86 20 3222 5275
✉ info@promat.com.cn

Hong Kong

Promat International (Asia Pacific) Ltd

Room 1010, C.C. Wu Building
302-308 Hennessy Road,
Wanchai
☎ +852 2836 3692
✉ promat.hk@etexgroup.com

Malaysia

Etex Malaysia Sdn Bhd

(Formerly known as Promat (Malaysia) Sdn. Bhd.)
Unit 19-02-01, Level 2, Wisma Tune
19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
☎ +60 3 2095 8555
✉ promat.my@etexgroup.com

Singapore

Promat Building System Pte Ltd

10 Science Park Road, #03-14 The Alpha
Singapore Science Park II
117684 Singapore
☎ +65 6776 7635
✉ promat.sg@etexgroup.com

www.promat.com

- The technical data provided in this publication is based on mean values prevalent at time of publication and is thus subject to fluctuation. It should not be regarded as a guarantee to system performance.
- All data contained herein conforms to and frequently surpasses generally accepted fire protection standards recognised by most professional fire science practitioners and regulatory authorities worldwide. The same general principle is equally applicable to all Promat products and systems. Promat has access to a considerable body of test authentication data and this can be provided on a complimentary basis upon request. It should be noted however that this publication replaces all previous editions in its entirety.
- This document is protected by International copyright laws. Reproduction and distribution in whole or in part without prior written permission is strictly prohibited. PROMAT, PROMATECT and logo are registered trademark of Etex NV or an affiliate thereof in Asia Pacific and/or other countries. Any use without authorisation is prohibited and may violate trademark laws.